

**SECTION 703**  
**AGGREGATES**

*Add new subsection 703-2.15.*

**703-2.15 CRUSHED GLASS.** Up to 10% by weight crushed glass (cullet) smaller than 3/8-inch may be uniformly blended with natural soil-aggregate material prior to project delivery and placement. Glass cullet must be free of soil, paper, plastic, metals, organic material and other deleterious and hazardous substances. No more than 2.0% debris should be present as determined by Section X3 of AASHTO M318.

Eligible glass products from which glass cullet might be produced include: food and beverage container glass; plain ceramic or china dinnerware; or building window glass.

Prohibited glass products include: automobile windshields or other glass from automobiles; light bulbs of any type; porcelain products; laboratory glass; television, computer or other cathode ray monitor tubes.

Provide documentation certifying that the glass cullet:

1. Showing the origin of the glass products,
2. Does not contain prohibited materials,
3. Meets debris content requirement.

Uniformly blend glass cullet and natural soil-aggregate and meet the following gradation requirements for the type specified:

**TABLE 703-13**

<b>Type (Section)</b>	<b>Section/Table</b>
Selected material (203-3.03)	Section 703-2.07
Base course (301)	Table 703-2
Subbase (304)	Table 703-8

For the natural soil-aggregate used in the blend, meet quality requirements as shown in Table 703-1, Section 703-2.07, or Section 703-2.09 for the type specified.