



Wall Mix

Flex-c-ment™ Wall Mix is a Polymer Modified Cementitious Vertical Overlay System.

Manufactured and Distributed by: Consolidated Aggregates, LLC

1205 Palestine Road, Picayune, Mississippi 39466

A. COMPOSITION

Flex-c-ment™ Wall Mix is a polyacrylate, modified cementitious, vertical overlay system that can be applied over concrete, wood or metal to achieve the appearance stone, wood, tile or brick. It is a water-phase elastomeric resin composition incorporating resin primers, cement, cement modifiers, polymers and aggregates. The components are supplied in a dry, 50 Lb. bagged mix of cement, light weight aggregates and additives and polymers. All ingredients are prepackaged in the 50 Lb. bag. It is a "just add water" mix.

B. USES

Flex-c-ment™ Wall Mix is typically used as a decorative wall overlay for surfacing in both commercial and residential applications. Its use can be enhanced by incorporating the use of pigments, stains and sealers to finish the coloring and sealing process.

Flex-c-ment™ Wall Mix can be used as a thin overlay for use with stencils or free style finishes or in full 2 1/2 inch thickness with stamps, trowels, carving tools, brushes, sprays or it can be worked freehand to achieve an incredible variety of decorative surfaces.

C. CAUTIONS

Flex-c-ment™ Wall Mix must be installed over a stable substrate, with normal movement due to expansion and contraction, using proper preparation and installation procedures. All expansion/cut joints in the existing substrate must be honored. Extra joints may be added as deemed necessary by the installer.

Flex-c-ment™ Primer must be used with the Flex-c-ment™ Wall Mix and is required for the Flex-c-ment™ warranty to be valid. It has been chemically engineered to be compatible with Flex-C-Ment products to provide the maximum physical properties and prevent loss of bond to the substrate.

D. PHYSICAL PROPERTIES

1. **Compressive Strength** ASTM C 39 2,640 psi
2. **Flexural Strength** ASTM C 78 515 psi
3. **Adhesion** MIL-D-3134 Para. 3.7.14 (Shear from steel plate after 96 hours ... 312 psi
4. **Water Absorption** ASTM C 642 4.2%
5. **Tensile Strength** ASTM C190 580 psi
6. **Resistance to Elevated Temperatures** MIL-D-3134, Para. 4.7.5.1.... No flow or Slip
7. **Flammability** ASTM E162 Flame Spread Index. 0.47. Smoke Deposited. Less than 0.1 mg. ASTM E84.. Flame Spread Rate - 0, Smoke Density Factor - 3, Fuel Contribution Rate - 0
8. **Coefficient of Thermal Expansion** ASTM C531 6.8 E-04
9. **Electrical Conductivity** Dielectric
10. **Freezing and Thawing** ASTM C 666/C 666M-03 (Standard Test Method for Resistance of Concrete to Freezing and Thawing, Procedure A - Freezing and Thawing in Water) The relative dynamic modulus indicates that Flex-c-ment™ Wall Mix is freeze-thaw durable after 300 cycles.

Modified ASTM C 666 - Procedure A

Standard Test Method for Resistance of Concrete to Rapid Freezing and Thawing¹

Sample Identifications	Freeze-Thaw Cycles	Length Change, %	Mass Change, %	Relative Dynamic Modulus, %
	0	0.00	0.00	100
	37	0.01	- 0.22	97
	69	0.02	- 0.40	95
	99	0.03	- 0.56	97
Wallmix 1, 2 and 3	129	0.02	- 0.62	94
	163	0.03	- 0.45	93
	193	0.02	- 0.50	98
	222	0.02	- 0.58	98
	232	0.03	- 0.63	98

Product Technical Data Sheet

Benefits:

- Many Methods of Application, i.e., Stencils, Stamps, Carved Troweled or Freehand
- Can be Hand Carved for up to 24 Hours.
- Can be Applied from Thin Featheredge to Deep Fill
- Lightweight Allows Increased Stamp Depth and Design Features
- Can Withstand Normal Surface Movement with Minimal Negative Effects
- Very Cost Effective
- Easily Applied over Problematic Surfaces with Little Surface Preparation.
- Continuous System, No Mortar Joints to Deteriorate
- No Moisture or Insect Intrusion
- Low Maintenance Costs.
- Wide Range of Textures and Colors.
- Water Clean-up.

E. CLEANABILITY

In general, the more aggressive the finished surface the more difficult to clean. The smoother the finished texture the easier the surface is to clean. Cleaning and disinfecting compounds and cleaning techniques can affect the color, gloss, texture and performance of the system. As a precautionary step, Flex-c-ment™ recommends that the end-user test their cleaning and disinfecting compounds on a non-conspicuous area before use.

If sealers are used, follow sealer manufacturer recommendations for maintenance and cleaning.

F. COVERAGE

Approximate Surface Area Coverage per Bag:

Applied Thickness:

Coverage:

1/4 "

24 Square Feet

1/2"

12

3/4"

8 Most Commonly Applied Thickness. Accommodates Wide Range of Designs

2"

3

G. SHELF LIFE

If properly stored the expected shelf life can exceed 6 months. However; it is recommended that Flex-c-ment™ Overlay Mix be used as soon as possible after delivery. Rotate stock to use oldest inventory first. Store under roof and keep dry.

LIMITED WARRANTY:

NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN Flex-c-ment™ - Consolidated Aggregates, LLC . INVOICE ARE MET.

Flex-c-ment™ warrants to the purchaser of its products that such products are free from manufacturing defect. Flex-c-ment™ does not warrant or guarantee the workmanship performed by any person or firm installing its products. Flex-c-ment™'s obligation under this warranty is limited solely to the original purchaser and solely to replacement in kind of any Flex-c-ment™ product which may prove defective in manufacture within three years from date of installation, provided said product was stored correctly and installed within the product's shelf life, by the original purchaser and upon examination, by Flex-c-ment™, shall be deemed defective.

IN NO EVENT SHALL Flex-c-ment™ BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON Flex-c-ment's™ PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF A Flex-c-ment™ PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF Flex-c-ment™ PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION, ABUSE OR MISUSE. Flex-c-ment™ MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIALS NOT SUPPLIED BY Flex-c-ment™, WHICH ARE USED IN CONNECTION WITH ITS PRODUCTS. THE TERM "ORIGINAL PURCHASER" IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM Flex-c-ment™ PRODUCTS CORP. SOLD ITS PRODUCT OR PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST Flex-c-ment™ SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES.

DECORATIVE CONCRETE SUPPLY,
LLC.

Shane Perrins
Owner

1310 E. 66th Ave. Ste. #3
Anchorage, AK 99518
(907) 230-6544
fax (907) 677-3931
shaneperrins@yahoo.com