

SECTION 203

EXCAVATION AND EMBANKMENT

203-2.01 MATERIALS. *Add to the end of this subsection.*

6. Crushed Glass: May be combined with soil-aggregate material to be used in embankment construction. Meet 703-2.15 requirements.

203-3.01 GENERAL. *Add to the end of this subsection.*

Do not place soil-aggregate containing glass cullet:

1. Within four feet from the face of any embankment slope,
2. Within 150 feet from any surface water body,
3. In embankment areas where culvert placement is required,
4. In contact with any geosynthetic material.