## SECTION 401 HOT MIX ASPHALT PAVEMENT

## Add the following subsection:

**401-3.21 ASPHALT SAFETYEDGE<sup>SM</sup>**. Incorporate asphalt **SAFETYEDGE<sup>SM</sup>** to the dimensions shown as designated in the Plans. Construct the asphalt **SAFETYEDGE<sup>SM</sup>** monolithically with the HMA. Comply with all Construction Requirements set forth in Section 401.

Utilize an approved asphalt **SAFETYEDGE<sup>SM</sup>** system that is capable of providing a sloped wedge equal to the dimensions shown in the Plans. The use of a single plate strike off is not allowed. The asphalt **SAFETYEDGE<sup>SM</sup>** system must be adjustable to accommodate varying paving thicknesses. All asphalt **SAFETYEDGE<sup>SM</sup>** systems to be used must be approved by the Engineer.

Construct a 100-foot test section prior to work to demonstrate the edge shape and compaction. Make adjustments as required by the Engineer to meet specification requirements.

## 401-4.01 METHOD OF MEASUREMENT. After item 14, add the following:

15. <u>Asphalt</u> **SAFETYEDGE<sup>SM</sup>**. The additional work required to construct the asphalt **SAFETYEDGE<sup>SM</sup>** and test section will not be measured for payment.